




SAULEDA, S.A.  
Travessera de les Corts, 102  
08028 Barcelona (Spain)  
Tel. +34 933 397 150  
Fax +34 934 111 290  
sauleda@sauleda.com  
www.sauleda.com



6650 TEXILIFE



6647 TEXILIFE PLUS

Características técnicas • Technical characteristics • Caractéristiques techniques • Technische Date

	Texilife	Texilife Plus
Tejido • Fabric • Tissu • Gewebe	Polyester AT 1100 dtex	Polyester AT 1100 dtex
Peso • Weight • Poids • Gewicht	670 gr/m <sup>2</sup>	780 gr/m <sup>2</sup>
Ancho • Width • Largeur • Breite	300 cm	300 cm
Espesor • Thickness • Épaisseur • Dicke	0,53 mm	0,65 mm
Resistencia tracción • Tensile strength	300 daN/5cm	300 daN/5cm
Résistance à la rupture • Höchstzugkraft	280 daN/5cm	300 daN/5cm
Resistencia desgarre • Tear strength	30 daN	40 daN
Résistance à la déchirure • Weiterreissfestigkeit	25 daN	40 daN
Adherencia • adhesion • Adhérence • Haftung	10 daN/5 cm	10 daN/5 cm
Longitud de las piezas • Roll length • Longueur des pièces • Rollenlänge	50 ml	50 ml

APLICACIONES • APPLICATIONS • APPLIKATIONEN

Agua potable • Piscifactorias • Fish farms • Drinking water • Piscicultures • Eau potable • Fischzuchtbetriebe • Trinkwasser

